

Blockout

Blockout

Gloaming



By HanDe

Product Certificate

Fire, Smoke Classification	Non-FR FR(US) - NFPA 701 TM#1 (By Request)	
Health & Safety	Greenguard® Gold RoHS Directive (EU)2015/863 AATCC112-2014	EN71 Part 3:1994 GB18586 - 2001
Colour fastness to light	≥Grade 6 ISO105 B02:2014 ≥4.0 AATCC TM 16.3-2014; Option 3; Xenon Arc Lamp	
Warranty	5 Years	



Technical Data

STYLE		Gloaming
Composition		100% Polyester coated with Acrylic
Openness Factor		0%
UV Screen		100%
Width	Inch	118"
	cm	300
Weight	oz/yd ²	8.85 ± 5%
(ISO 2286-2)	g/m ²	300 ± 5%
Thickness	Inch	0.014 ± 5%
(ISO 2286-3)	mm	0.35 ± 5%
Mechanical Resistance		
Breaking	Warp	≥990 N/5cm
(ISO 13934-1)	Weft	≥920 N/5cm
Tear	Warp	≥40 N
(ISO 4674)	Weft	≥50 N
Packing		32.8 yards
(Roll Length)		30 lm

Care & Cleaning


- ✧ Remove dust with vacuum cleaner or compressed air.
- ✧ Handle the fabric with care (clean and dry hands, or use of gloves).
- ✧ Do not scrub, use a plant-based eraser to remove superficial stains.
- ✧ Do not use solvents or any abrasive substance that might damage the coating of fabric.
- ✧ All types of chemicals will cause permanent damage to the fabric. Therefore, if cleaning windows etc., the blind will have to be raised to avoid any direct or indirect spray or splatter of chemicals on the fabric.

Fabrication


- ✧ Cutting: Cold ,Crush.
- ✧ Welding: Heat impulse,high-frequency.
- ✧ For fabrics with a white acrylic coating on one side, it is recommended to handle it on a clean dust-free and dry surface.
- ✧ Recommendations for Handling: For an easier handling of wide width fabric and to avoid having marks on it, recommends to roll the panel(s) onto a tube at each stage of the making-up.



Colours




GL0101 White




GL0102 Linen




GL0105 Pewter




GL0107 Pearl



GL0106 Bronze



GL0103 Grey



GL0104 Black



Hande[®]

Guangzhou Hande New Materials Co.,Ltd.

Add: No.161, Yao TianHe Street,Yong shun Avenue,Yonghe Economic Zone,
GZ Economic&Technological Development District, Guang zhou, China

Tel: 86-20-32226319 Fax: 86-20-32222205 PostCode: 511356

Email: info@handegroup.com.cn www.handegroup.com.cn